



Fosroc® Primer 7

Primer for Thioflex joints sealants

Uses

Primer 7 is used to prime prepared concrete joint edges prior to the installation of Thioflex 600 Gun Grade and Thioflex 600 Pouring Grade polysulphide joint sealants.

If the joints are to be immersed or subject to long term moisture, then Primer 13 should be considered.

Advantages

- Fast drying - enables sealant work to progress
- Single component - no mixing required

Description

Primer 7 is a low viscosity one component solvent based priming system for concrete joints prior to the installation of Thioflex 600 joint sealants.

Technical Support

Parchem offers a comprehensive range of high quality, high performance construction products. In addition, Parchem offers technical support and on-site service to specifiers, end-users and contractors.

Properties

Appearance:	Amber clear liquid
Cure time (touch dry):	30 mins @ 23°C

Instructions for Use

Preparation

All surfaces must be free from old joint sealants, oil, grease, free standing water or any loosely adherent material.

Application

The ambient and substrate temperature needs to be above 5°C before and after the application of the primer. Agitate the primer contents thoroughly by shaking the can for 30 seconds. Apply an even coat of primer by brush onto the bonding faces of the concrete, the base of the joint should have no primer residue present after the primer has been applied, then allow the primer to become touch dry before applying any sealant (typically 30 minutes at 23°C). **DO NOT APPLY SEALANT TO TACKY OR WET PRIMER.** The sealant must be applied within 8 hours at normal temperatures.

Cleaning

All tools and equipment should be cleaned immediately after use with Fosroc Solvent 10. Spillages should be absorbed with sand or sawdust and disposed in accordance with local regulations.

Estimating

Supply

Primer 7 (1 litre):	FC965209-1L
---------------------	-------------

Coverage

As a guide, 1 litre of Primer 7 will be required for each 30 litres of sealant, depending on concrete porosity.

Shelf Life

Primer 7 has a shelf life of 12 months from date of manufacture if kept in a dry, cool store in the original packs. Refer to the Use by Date indicated on the packaging.

Important notice

A Safety Data Sheet (SDS) and Technical Data Sheet (TDS) are available from the Parchem website or upon request from the nearest Parchem sales office. Read the SDS and TDS carefully prior to use as application or performance data may change from time to time. In emergency, contact any Poisons Information Centre (phone 13 11 26 within Australia) or a doctor for advice.

Product disclaimer

This Technical Data Sheet (TDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this TDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the manner in which, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Parchem does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether or not in accordance with any advice, specification, recommendation or information given by it.